

Installation Guidelines

USE ON:

Properly primed interior walls and ceilings, properly cured and primed plaster (below 10 pH), masonry, woodwork and metal. Sheen at 60°, 50-60.

LIMITATIONS:

Safecoat paints are made without formaldehyde preservatives. Do not contaminate. **Do not use when indoor temperature is below 55 degrees F. Do not freeze.**

SURFACE PREPARATION:

Ideal painting conditions include: dry surface, fresh air flow, 30-70% relative humidity, 55° to 85° F. Clean surfaces of dirt, grease, mildew and oil. Surface should be completely dry before application.

COVERAGE:

One gallon covers approximately 300-400 based on surface porosity.

APPLICATION:

Stir well before use; then apply with brush, roller or airless sprayer. Always wear painters mask when spraying. **Thick application, high humidity or conditions other than normal will cause Safecoat to dry and cure more slowly.**

Spraying Instructions:

- Reduce with up to 1/2 pint of water/gallon as needed.
- Airless sprayers should use 17/1000 to 21/1000 tip
- Reversible tips are best
- Use only 30 mesh high pressure filters
- For best coverage, spray 18" from surface
- Overlap preceding coat with 1/4 to 1/2 the fan width.

DRYING/CURING TIME:

For best results wait a minimum of 4 hours before recoating. This product cures and bonds over a full 7 day period.

HEALTH PRECAUTIONS:

As with all coatings and sealers, keep container tightly closed and out of the reach of children. Do not take internally. Always use adequate ventilation.

CLEAN-UP:

Clean tools and equipment while they are still wet with a warm soapy water solution. Any unused paint should be stored in air tight container for reuse. Or, add kitty litter to solidify in the can or roll out on a piece of cardboard and leave to dry before disposing. Do not flush excess paint down the sink or toilet.

PHYSICAL DATA

Physical Description: Low odor, mildly alkaline, white
Solubility in Water: Dilutable
VOC Material: 0 g/l
HAP's (Hazardous Air Pollutants) zero

If you are chemically sensitive, always test for personal tolerance.

Test samples available here:
www.greenbuildingsupply.com

